Growth and characterisation of ceria thin films and Ce-doped γ - Al_2O_3 nanowires using sol-gel techniques

S Gravani^{1,2}, K Polychronopoulou¹, V Stolojan², Q Cui³, P N Gibson⁴, S J Hinder², Z Gu³, C C Doumanidis¹, M A Baker^{2,*} and C Rebholz¹

¹*Mechanical and Manufacturing Engineering Department, Engineering School, University of Cyprus, 1678, Nicosia, Cyprus*

²*Faculty of Engineering and Physical Sciences, University of Surrey, Guildford, GU2 7XH, UK*

³*Department of Chemical Engineering and CHN/NCOE Nanomanufacturing Center, University of Massachusetts Lowell, Lowell, MA 01854, USA*

⁴*Institute for Health and Consumer Protection, Joint Research Centre of the European Commission, 21027 Ispra (VA), Italy*

*E-mail: M.Baker@surrey.ac.uk

ABSTRACT

γ - Al_2O_3 is a well known catalyst support. The addition of Ce to γ - Al_2O_3 is known to beneficially retard the phase transformation of γ - Al_2O_3 to α - Al_2O_3 and stabilise the γ -pore structure. In this work, Ce-doped γ - Al_2O_3 nanowires have been prepared by a novel sol-gel/hydrothermal pore sealing method employing an anodic aluminium oxide (AAO) template in a 0.01M cerium nitrate solution assisted by urea hydrolysis. Calcination at 500 °C for 6 hours resulted in the crystallisation of the Ce-doped AlOOH gel to form Ce-doped γ - Al_2O_3 nanowires. Ce^{3+} ions within the nanowires were present at a concentration of < 1 at. %. On the template surface, a nanocrystalline CeO_2 thin film was deposited with a cubic fluorite structure and a crystallite size of 6-7 nm. Characterisation of the nanowires and thin films was performed using SEM, TEM, EELS, XPS and XRD. The nanowire formation mechanism and urea hydrolysis kinetics are discussed in terms of the pH evolution during the reaction. The Ce-doped γ - Al_2O_3 nanowires are likely to find useful applications in catalysis and this novel method can be exploited further for doping alumina nanowires with other rare earth elements.

Keywords: AlOOH , γ - Al_2O_3 , Ce-doped, nanowires, thin film, sol-gel, AAO

1. Introduction

Aluminium oxide is one of the most widely used catalyst supports on an industrial scale, due to its low cost and high surface area [1]. However, the most catalytically-active phases, such as γ - and γ - Al_2O_3 present problems at high temperatures due to phase transformations. The transition from γ - Al_2O_3 to α - Al_2O_3 , leads to a considerable reduction of the surface area, causing a degeneration of the catalytic activity [2]. Thermal stability can be enhanced by retarding or delaying phase transitions and it has been shown that rare earth element additions, such as Ce, not only will retard the phase transformation from γ - Al_2O_3 to α - Al_2O_3 , but will also stabilise the pore structure of alumina [2-4].

CeO₂ is one of the most reactive rare-earth metal oxides and has been used as a promoter or support in industrial catalytic processes. Due to its high oxygen storage capacity (OSC), associated with rich oxygen vacancies and low redox potential between Ce³⁺ and Ce⁴⁺, and due to its good ion conductivity, thermal stability and strong ultraviolet light absorption, CeO₂ has been utilised in three-way-catalysis [5,6], solid oxide fuel cells (SOFC) [7], solar cells [8], UV blocking [9], gas sensing [10] and corrosion protection [11].

The technological properties of a catalyst strongly depend on the hydrothermal stability and texture of the support. Consequently, the specific surface area, pore size and shape and any chemical or physical modifications which result in a more stable material are of great importance. Furthermore, nanostructured materials exhibit interesting characteristics owing to their shape-specific and quantum size effects. In the case of catalyst supports for example, the high surface areas associated with 1-dimensional nanostructures will always enhance adsorption and catalytic properties [12]. For this reason, to date, several reports have described the synthesis of amorphous, boehmite (AlOOH) or γ -Al₂O₃ nanostructures, which most typically involve hydrothermal treatments [13-16] or through-etching of porous alumina templates [17-19]. Surprisingly, although the beneficial effects of lanthanide additions to the thermal and structure stability of γ -Al₂O₃ have been successfully demonstrated, studies describing the synthesis of Ce-doped γ -Al₂O₃ nanowires, have not been reported for sol-gel or other solution-derived γ -Al₂O₃ nanomaterials (particles, membranes).

Here, we have employed a novel combination of a traditional sol-gel treatment with the hydrothermal pore sealing phenomenon which occurs in anodic aluminium oxide templates. The templates are hydrothermally treated in hot water [20-22] to form AlOOH nanowires inside the template pores. However in this work, the “pore sealing” occurs while treating the template in a cerium nitrate solution, which doubly serves to form AlOOH but also to incorporate Ce. Urea added in the solution increases the amount of OH⁻ available for the precipitation of both cerium and aluminium hydroxides. Also, as a conventional sol-gel technique, the process allows the formation of a CeO₂ thin film. This novel synthesis method offers interesting possibilities for the formation of a selection of technologically interesting metal A doped - metal B oxide nanowires with varying compositions and structures.

2. Experimental details

2.1 Anodic aluminium oxide templates

High-purity Al sheets (99.999%, Advent Materials, 250 μ m thick) were ultrasonically cleaned in acetone for 15 minutes, etched in a 1M NaOH to remove the native oxide and washed thoroughly with distilled water. The pre-treated sheets were electropolished in a mixed solution of HClO₄:CH₃CH₂OH=1:4 (V/V) for 5 minutes and immediately washed with distilled water. The samples were anodised in a suitable electrolytic cell in which a 4.15cm² surface area of the Al sheet was exposed to the electrolyte and a Pt mesh was used as a cathode. The potential was applied using a Keithley 2300 power supply-interfaced with a PC, to monitor the current-time transient during the process. Anodisation was performed in a vigorously stirred solution of 0.3M H₂C₂O₄, under a constant voltage of 40 V at 25 °C for 2, 10 or 12 hours. Subsequently, pore-widening of the samples was carried out in a 5 vol. % H₃PO₄ solution at 25 °C for 30 minutes.

2.2 Nanowire and thin film preparation

All chemical reagents used were analytical grade. The precursor solution contained 0.01M cerium nitrate (Ce(NO₃)₃·6H₂O) (Sigma Aldrich) in distilled water. Urea was added to the solution, so that the metal precursor/urea molar ratio was 1/40. A clear solution was produced, which was then heated at 90°C while being vigorously stirred. AAO membranes were immersed into the solution for 8 hours while the temperature was kept at 90°C. The pH and temperature were measured throughout the sol-gel treatment using a Mettler Toledo pH electrode. Finally the samples were air-dried overnight and then calcinated at

500 °C, for 6 hours, with an initial heating rate of 10 °C/min.

2.3 Characterisation

The morphology was characterised by scanning electron microscopy (SEM) with both Tescan Vega and JEOL 7401F microscopes operated at a 30 kV incident electron beam voltage. Prior to SEM characterisation, the filled template samples were etched in 1M NaOH for 8 minutes and carefully washed with distilled water in order to selectively dissolve the AAO and expose the nanowires which were assembled in the template. Subsequently, both of the samples containing the nanowire and the thin film were sputter-coated with 8 nm of Au. In order to observe the morphology and the degree of agglomeration, transmission electron microscope (TEM) images were taken with a Philips CM200 TEM (LaB₆) and Hitachi 2300A STEM (Schottky), both operated at 200 kV. SEM and TEM samples were prepared by loosening the nanowires from the template by partially dissolving the AAO in 0.25M NaOH solution, for 10 minutes. Then each template surface was scratched by a flat-tip tweezer and the material that was peeled from the surface was placed again in 0.25M NaOH for 10 more minutes, to completely dissolve any Al₂O₃ remnants. The isolated nanowires were washed three times with deionised water and then ethanol, and were kept dispersed in ethanol solution for further characterization. TEM samples were prepared by drop casting a nanoparticle dispersion (in ethanol) onto copper grids coated with a Formvar and carbon film (200 mesh, SPI, West Chester, PA) for TEM characterisation and on Si wafers for SEM characterisation. Electron energy loss spectroscopy (EELS) was undertaken using the Gatan Imaging Filter on the TEM and a Gatan Enfina spectrometer on the STEM. Point-by-point analysis was performed in the STEM with a 2.5Å-diameter electron beam, using Gatan's Spectrum Imaging tool, with a probe convergence semi-angle of 14mrad and 16mrad collection semi-angle; the energy spread of the beam was 0.8eV FWHM. X-ray diffraction (XRD) data were recorded using an in-house developed glancing angle XRD (GAXRD) system at the European Commission's Joint Research Centre, Ispra, Italy. The diffractometer has a laser alignment system for determination of incident angle, an instrumental resolution of about 0.2°, a solid state detector for improved signal/noise ratio, and operates with a Cu-K α X-ray source (λ =1.5418 Å). All GAXRD scans were measured at an incident angle of 1°. Crystallite grain sizes were determined using the single-line method of de Keijser, based on the least-squares fitting of broadened peaks to a pseudo-Voigt function [23]. X-ray photoelectron spectroscopy (XPS) data were recorded on a VG ESCALAB mk II, employing a non-monochromated Al K α source operated at 12 kV and 30 mA and hemispherical analyser. The binding energy was charge referenced using the C 1s hydrocarbon contamination peak at 285.0 eV. Wide scan spectra were recorded at a pass energy of 100 eV and elemental peaks at a pass energy of 20 eV. The energy resolution for the elemental narrow scans was 0.5-0.6 eV. Prior to analysis samples were etched using a 3kV 1 μ A Ar⁺ beam for 30 seconds in order to reduce the surface carbon contamination.

3. Results

The in-house prepared AAO templates were examined to determine their geometrical characteristics, prior to being used in nanowire synthesis. SEM analysis indicated that a typical template is 70 μ m thick and has pores that vary between 50-70 nm, at a density of 4×10^{10} pores /cm². The process overview for the thin film and nanowire formation is summarised schematically, together with SEM micrographs from each of the different stages in Figure 1. The prepared template (figure 1a) was treated in a temperature-controlled urea hydrolysis sol-gel method, with cerium nitrate as the precursor material. During the process, Ce-containing aluminium oxy-hydroxide precipitated inside the pores, filling them completely and causing pore sealing, as seen in figure 1b. A Ce(OH)₄ gel was subsequently deposited, on top of the sealed AAO template. Following calcination and partial etching of the template in NaOH, the thin film and nanowires were evident (figure 1c). Finally, the AAO was completely dissolved in order to collect nanowires for further characterisation. Figure 1d shows isolated nanowires mounted on a Si wafer.

Figure 1. Schematic representation of the thin film deposition and nanowire formation paired with SEM images: (a) Plan view of a typical porous alumina template; (b) Filled template after the sol-gel treatment; (c) CeO₂ thin film and Ce-doped γ -Al₂O₃ nanowires following calcination at 500 °C and etching in NaOH to partially remove the AAO template; (d) Free-standing nanowires on a Si wafer after detachment from the Al substrate and complete dissolution of the AAO.

3.1 Thin film

The sol-gel deposited thin film was characterised further to examine its structure. Figure 2 shows a GAXRD pattern of the CeO₂ thin film deposited on the AAO template. The sample exhibits peaks that correspond to the (111), (200), (220), (311), (222), (400), (331), (420) and (422) planes of the cubic fluorite structure (space group: Fm3m) of CeO₂, as identified from standard data (JCPDS 34-0394). The CeO₂ lattice parameter calculated from this pattern is in very close agreement (within 0.02%) with that of the JCPDS value for bulk CeO₂ ($a=5.4113$). The crystallite size of the film was found to be ~6-7 nm and is close to the expected value for sol-gel materials derived at calcination temperatures of up to 700 °C [24].

Figure 2. GAXRD pattern at 1° incident angle of CeO₂ thin film deposited by sol-gel on the AAO template.

The chemical state of Ce in the thin film was also investigated by XPS. Figure 3 illustrates the XPS spectra of the deposited film obtained after argon ion etching its top surface for 30 seconds. From the Ce 3d core-level spectra (figure 3a), six Ce 3d_{5/2} binding energy peaks are identified at 882.6, 889.2, 898.6, 901.2, 907.8 and 917 eV, corresponding to v, v2, v3 and u, u2, u3 components, as reported by Ardelean *et al* [25] and Rao *et al* [26] for Ce⁴⁺. No Ce³⁺ peaks were observed. It should be noted that the binding energies are shifted to slightly higher values (0.2-0.4 eV) compared to those reported by Rao *et al* [26], as the C 1s hydrocarbon peak was referenced to 284.6 eV in the paper of Rao *et al* compared to the 285.0 eV hydrocarbon reference used in this work and that of Ardelean *et al* [25]. In the O 1s spectra (figure 3b), the peak splits into two separate components, of which the lower binding energy component (529.3 eV) originates from lattice O²⁻ and the higher binding energy component (531.3 eV) can be ascribed to OH⁻ groups on or near the surface of the sample [27].

Figure 3. (a) Ce 3d and (b) O 1s XPS spectra of the sol-gel deposited CeO_2 thin film obtained after Ar^+ etching for 30 seconds.

3.2 Nanowires

The morphology and the structure of the synthesised nanowires were examined in detail. Figure 4 is a typical SEM image of the Ce-doped $\gamma-Al_2O_3$ nanowires which were obtained after the partial dissolution of the AAO template in NaOH. A high density of nanowires is evident, each nanowire being many microns in length. The morphological characteristics of the nanowires were more closely examined using TEM. Example TEM images of free-standing nanowires, after completely etching away the AAO template in NaOH, are shown in figures 5a and b. The nanowires have a uniform thickness and structure. The high magnification image, figure 5b, shows that the nanowire is approximately 50 nm in diameter. It has a “coarse” texture and its bulk consists of apparently randomly oriented nanocrystallites. SEM and TEM characterisation revealed that the nanowires were up to tens of microns in length, with diameters of 50 - 70 nm. Their diameter distribution is in close agreement with the pore sizes of the applied AAO template.

Figure 4. SEM image of high aspect ratio Ce-doped $\gamma-Al_2O_3$ nanowires after the partial removal of the AAO template.

Figure 5. TEM bright field images: (a) a bundle of nanowires; (b) high magnification image of a single nanowire.

Compositional analysis of the nanowires was examined through EELS. Figure 6a shows a small group of nanowires indicated on the image as area (B) and a nanoparticle as (A). EELS analysis performed in each location revealed that the nanowires consisted largely of Al and O and that the particle was a CeO_2 fragment, most probably originating from the sol-gel surface layer. The EELS Ce $M_{4,5}$ edge obtained directly from the nanoparticle is presented in figure 6b and represents transitions from the spin-orbit split 3d-orbital to empty states in the 4p and 4f-orbitals, with the transitions to 4f dominating due to the much higher cross-section than that of transitions to 4p. The shape is consistent with that given by Garvie and Buseck [28] and other authors [29,30] for Ce^{4+} (CeO_2). The Ce^{4+} M_5 and M_4 edges consist of two maxima separated by 17.6 eV (indicated as A and A' in figure 6b), that correspond to electron transitions from the $3d_{5/2}$ and $3d_{3/2}$ respectively. The M_5 maximum has been aligned to that given by Garvie and Buseck at 884.0 eV [28]. The M_5 and M_4 peaks are further degenerated, with small satellite peaks on the high energy side (indicated as B and B' in figure 6b) at 889.3 and 906.5 eV respectively, assigned to crystal-field splitting. The high-resolution TEM image (figure 6c) shows the presence of crystallites, with a lattice fringe spacing which is consistent with that of bulk CeO_2 ($d_{111}=3.12\text{\AA}$) and a selected area electron diffraction (SAED) pattern taken of a similar particle together with surrounding nanowires (figure 6d) shows reflections assignable to CeO_2 . Hence, we concluded that this nanoparticle is a fragment of the CeO_2 sol-gel deposited thin film.

Figure 6. (a) TEM image of nanoparticle and nanowires (b) EELS Ce $M_{4,5}$ edge spectra of nanoparticle (c) HRTEM image of nanoparticle (d) SAED pattern obtained from area as presented in (a).

The crystalline nature of the nanowires was investigated by SAED and bright- and dark-field imaging. As mentioned above, Figure 6d shows a SAED from an area containing both a CeO_2 nanoparticle and a group of nanowires. In addition to the CeO_2 reflections, other diffraction rings could be assigned to the $\gamma\text{-Al}_2\text{O}_3$ phase. (figure 6d). The corresponding bright- and dark-field TEM images in figure 7 clearly show the nanocrystalline nature of the nanowires, with the average $\gamma\text{-Al}_2\text{O}_3$ grain size being 2-3 nm. The dark-field image was obtained by forming an image with the 400, 222 and 311 reflections of $\gamma\text{-Al}_2\text{O}_3$ in figure 6d.

Figure 7. Bright field (a) and dark field (b) TEM images of nanowires.

To obtain more detailed information on the chemical composition of the nanowires, EELS data for Al, O and Ce, were recorded by scanning the beam across two nanowires, as shown in figure 8a. The EELS spectra generated for each element were integrated intensities from each point on the linescan. The thickness of the wires analysed in Fig. 8a is $\sim 0.4\lambda$ (where λ is the mean free path for inelastic scattering, which for alumina is 116 nm [31]) therefore correction of the spectra for thickness artefacts is not necessary. The spectra showed high intensity Al L-edge and O K-edge and a smaller Ce integrated M-edge signal. These high Al and O peak intensities are consistent with the identification of γ - Al_2O_3 in the SAED pattern of Figure 6(d). Figure 8b shows the integrated Ce $M_{4,5}$ edge from a single nanowire, corresponding to linescan A in figure 8a. The Ce $M_{4,5}$ edge shape and peak positions are significantly different from that of Ce^{4+} described earlier for the CeO_2 nanoparticle (superimposed on figure 8b with a dashed line). In particular, for the nanowire, the high energy satellites (labelled B and B' in figure 6b) characteristic of Ce^{4+} , are no longer present. The nanowire Ce $M_{4,5}$ peak shape is consistent with that reported by Garvie and Buseck [28] for Ce^{3+} (Ce_2O_3) and again the M_5 peak maximum in figure 8b has been aligned with their value of 882.0 eV. In addition to the peak shape, the intensity ratio between the M_5 and M_4 edges can also be used to determine the valence state of Ce [28]. In the nanowires examined here, the M_5/M_4 ratio across the nanowire was found to be 0.80 which is comparable to the 0.82 reported value for Ce_2O_3 and for the CeO_2 nanoparticle, the M_5/M_4 ratio of 0.60 is comparable to the reported value of 0.67 for CeO_2 [28]. Electron-beam damage is not the cause of this transformation [28], as acquiring several Ce M-edge spectra at the same place on several pristine nanowires did not show any significant change in the shape of the edge, but instead, simply a removal of material.

Figure 8. (a) STEM image indicating EELS linescan location; (b) Comparative EELS Ce-M_{4,5} edge for the nanowires (solid line) and CeO₂ nanoparticle (dotted line); (c) Comparative O/Al/Ce linescan intensities (displayed as core-loss signal instead of composition, due to the absence of a scattering cross-section for the Ce M edge. The Al and Ce intensities have been multiplied by a factor of 10 for presentation purposes).

With regard to establishing the Ce content in the γ -Al₂O₃ nanowires, quantification is problematic due to the absence of a reliable EELS cross-section for the Ce M-edge. However, utilising the EELS results from the CeO₂ nanoparticle, an experimentally determined value for Ce was evaluated. A second linescan (marked as B on figure 8a) was taken across two nanowires. Figure 8c presents the raw integrated intensities under the Al, O and Ce edges across the nanowires. The O intensity in both nanowires is similar. The Al intensity is high and Ce intensity low in the first nanowire. In the second nanowire, the Al intensity is slightly lower and Ce intensity slightly higher. This would suggest that there may be an inverse relationship between the Al and Ce intensities (possibly indicative of a substitution/exchange of Al and Ce within the nanocrystalline oxide structure), but more results would be required to confirm this. Due to the large energy-loss cross-section for the Ce M-edge, when quantified, the Ce concentration is found to be < 1 at.% and the Al:O atomic ratio approximately 2:3 in both nanowires.

4. Discussion

4.1 Formation of CeO_2 thin films

The GAXRD and XPS results presented in this work have shown that a nanocrystalline CeO_2 thin film, with a cubic fluorite structure and average grain size of 6-7 nm, can be successfully deposited using a sol-gel process, employing a 0.01M cerium nitrate solution containing urea, at a Ce:urea molar ratio of 1:40 and calcination at a temperature of 500 °C for 6 hours. The cerium nitrate-based sol gel process assisted by urea reported previously used a Ce:urea molar ratio of 20 and a reaction temperature of 80°C [32]. In this work the Ce:urea molar ratio was changed to 1:40 and the reaction temperature increased to 90-100 °C. The motivation for these changes to the previously reported process were as follows: the urea concentration was increased to raise the amount of OH^- available and increase the precipitation rate. The reaction temperature was increased to 90-100 °C in order to maximise the hydrolysis of the increased amount of urea.

4.2 Deposition of Ce-doped $\gamma\text{-Al}_2\text{O}_3$ nanowires

From SEM, TEM and EELS analysis, it has been shown that under the same process conditions which lead to the deposition of a CeO_2 thin film on top of a porous anodic alumina template, within the template, Ce-doped $\gamma\text{-Al}_2\text{O}_3$ nanowires are formed. The nanowires were up to tens of microns in length, with diameters of 50 - 70 nm. The $\gamma\text{-Al}_2\text{O}_3$ grain size is approximately 2-3 nm and Ce is found to be present as Ce^{3+} ions within the nanowires, at a concentration of < 1 at.%.

4.3. Sol-gel/hydrothermal pore sealing formation mechanism of the Ce-doped $\gamma\text{-Al}_2\text{O}_3$ nanowires

A cerium nitrate urea-assisted sol-gel technique has previously been applied to porous alumina templates by Wu *et al* [32], through which they obtained cubic-fluorite CeO_2 nanowires. In that work, although not explicitly stated, the porous alumina layer was detached from the aluminium substrate and was subsequently etched to widen the pores and perforate the hemispherical, scalloped geometry situated at the bottom of each pore. In our work, we have utilised the geometry of substrate supported, one-side, open-ended alumina templates, in order to hydrothermally pore seal during the sol-gel process and obtain Ce-doped $\gamma\text{-Al}_2\text{O}_3$ nanowires. The proposed formation mechanism of the Ce-doped $\gamma\text{-Al}_2\text{O}_3$ nanowires is described in the following sub-sections.

4.3.1. Hydrothermal pore sealing

Porous anodic alumina is considered to be generally amorphous and have a composition which varies from that of pure Al_2O_3 [33,34]. Both anions from the electrolyte and hydroxyl ions are incorporated into the amorphous anodic alumina structure [33]. XRD analysis of anodic films formed in a nitric acid have indicated that the amorphous alumina which forms resembles a cubic distorted $\gamma\text{-Al}_2\text{O}_3$ and hydroxyl ions are incorporated to form pseudo-boehmite (AlOOH) [34]. Hydrothermal pore-sealing can occur in water, water vapour or in this case, a 0.01M cerium nitrate:urea solution in a molar ratio of 1:40, heated and stirred at 90°C for 8 hours. Jha *et al* employed doubly-distilled water and proposed that, during the hydrothermal pore-sealing process, the water in the pores dissolves the amorphous alumina to form a gel which, upon saturation, precipitates as pseudo-boehmite or boehmite inside the pores [20]. In this work, the porous anodic alumina template is not treated in boiling water, but instead is undergoing a simultaneous sol-gel treatment in order to introduce Ce as well.

4.3.2. Sol-gel process

The sol-gel process involves the hydrolysis of a precursor molecule in solution to first obtain a suspension of colloidal particles (the sol) and then a gel composed of aggregate sol particles [12]. The hydrolysis of cations can be controlled by a slow release of hydroxide ions into the metal salt solution. This was achieved by the decomposition of an organic compound, in this case urea, which is a very weak Brønsted base, highly soluble in water and its hydrolysis can be controlled by varying the temperature. During the decomposition of urea, CO_3^{2-} and OH^- are produced, accompanied by an increase in the pH, leading to the

precipitation of metal basic carbonates and hydroxides.

The pH increase with time, as the reaction proceeds, is indicative of the hydrolysis kinetics and is shown in figure 9. Four distinct phases can be described. In phase I, the temperature is increasing to its stable value of 90 °C, the pH having a constant value of 5.4. (Reaction temperatures in the range of 90-100 °C allow the hydrolysis of urea at a high rate [35] and hence this temperature was used during the reaction to maximise precipitation). Following stabilisation at 90 °C, phase II is characterised by the hydrolysis of urea and the pH dropping to low values. This is followed by a release of OH⁻ (phase III) in which the hydroxyl ions react immediately with (i) the template pore walls to form aquo-hydroxo complexes (intermediate species for the precipitation of aluminium hydroxide) and (ii) with the cerium cations which become incorporated into the aluminium hydroxide (evidently at small amounts). Following successful pore closure, precipitation continues and a cerium hydroxide film forms on top of the AAO template. Phase IV is characterised by a high rate of OH⁻ consumption (high reaction rate) and leads to a stable pH.

Figure 9. Evolution of pH during the hydrolysis reaction.

With regard to the kinetics of AlOOH precipitation inside the template pores during the cerium nitrate solution treatment, it should be expected that this occurs more rapidly than for conventional hydrothermal treatments in water, due to the increased amount of available OH⁻ which assists the reaction process, expediting the precipitation of AlOOH.

TEM and SAED analysis have confirmed that the calcination process has resulted in the precipitated AlOOH being transformed into γ -Al₂O₃. This is in agreement with previous reports that γ -Al₂O₃ phase forms upon dehydration of AlOOH at temperatures between 400-700 °C [13,36]. Ce³⁺ ions from the 0.01M cerium nitrate solution have become incorporated into the nanowire structure.

4.3.3. Formation of free standing Ce-doped γ -Al₂O₃ nanowires

The SEM and TEM micrographs in Figures 4 and 5 show that exposure to 1M NaOH has resulted in the porous anodic alumina being dissolved, yielding free-standing Ce-doped γ -Al₂O₃ nanowires. This is consistent with the results of Mardilovich *et al*, in which they show that γ -Al₂O₃ is much more stable to acid and base attack than anodic amorphous alumina [38]. They propose that the presence of hydroxyl groups in the amorphous anodic alumina and specifically a structure with aluminium ions bonded to two terminal hydroxyl groups is more active in the etching process, leading to a poorer resistance to acids and bases.

4.3.4. Schematic representation of Ce-doped γ - Al_2O_3 nanowire formation

A schematic diagram of the different process steps in the Ce-doped γ - Al_2O_3 nanowire formation is presented in figure 10. Prepared AAO templates are immersed in the 0.01M cerium nitrate:urea solution (1:40 molar ratio) - figure 10a. Hydration of the pore walls leads to the formation of aquo-hydro complexes which upon saturation lead to the precipitation of Ce-containing aluminium oxy-hydroxide (Ce-AlOOH) which fills the pores and causes pore sealing - figure 10b. Following, hydrothermal pore sealing, calcination at 500 °C for 6 hours (figure 10c) leads to transformation of Ce-AlOOH to Ce-doped γ - Al_2O_3 (figure 10c). Etching in 1M NaOH allows the selective dissolution of the amorphous Al_2O_3 template and formation of free-standing Ce-doped γ - Al_2O_3 nanowires - figure 10d.

Figure 10. Plan view and cross-section schematic representations of the formation of Ce-doped γ - Al_2O_3 nanowires; (a) prepared AAO templates; (b) immersion of the AAO template in 0.01M cerium nitrate:urea solution (1:40 molar ratio) leads to hydration of the amorphous Al_2O_3 pore walls which upon saturation results in formation of Ce-containing aluminium oxy-hydroxide (AlOOH) and pore sealing; (c) calcination allows crystallisation of Ce-AlOOH to Ce-doped γ - Al_2O_3 ; (d) selective dissolution of the amorphous AAO allows formation of free-standing Ce-doped γ - Al_2O_3 nanowires.

4.4. Bonding of Ce in the Ce-doped γ - Al_2O_3 nanowires

The EELS results have shown that Ce is present in the nanowires as Ce^{3+} ions. It would be expected that the Ce^{3+} ions are bonding with O^{2-} ions to form Ce_2O_3 , but the exact location of the Ce^{3+} ions is not known. It might be expected that the large difference between Ce^{3+} (1.034 Å) and Al^{3+} (0.51 Å) would not lead to direct substitution, and hence the Ce ions may be segregating to more energetically favourable grain boundary sites within the nanocrystalline γ - Al_2O_3 nanowires. However, substitution of Al^{3+} by a rare earth 3+ ion could occur if there is a substantial rearrangement of the nearest neighbour environment to provide the necessary space. Kaplyanski et al [37] have observed the successful incorporation of rare earth 3+ ions such as Eu^{3+} , Er^{3+} , Pr^{3+} , via a sol-gel technique, in a distorted γ - Al_2O_3 lattice and after annealing above 900 °C also in γ - Al_2O_3 .

4.5. Further development of the sol-gel/hydrothermal pore sealing method

The described synthesis technique can be exploited further to obtain a range of technologically interesting metal A doped - metal B oxide nanowires with different compositions and structures through varying, the metal salt A (i.e. doping with other rare earth elements such as Y, La, Gd, Nd), the metal salt concentration (e.g. 1, 3, 5 at.%), the metal B oxide template material (e.g. titania) and also the annealing process to obtain different crystallographic forms of the metal B oxide such as γ -, β - and α -Al₂O₃ or anatase, brookite and rutile (TiO₂).

4.6 Possible applications of Ce-doped γ -Al₂O₃

Most industrial catalysts consist of active centres anchored on transition aluminas due to the high porosity, surface area, mechanical strength and thermal stability at moderate temperatures. At high temperature catalytic reactions (1000-1400 °C) the transition from γ -Al₂O₃ to α -Al₂O₃ leads to a considerable reduction of the surface area causing degeneration of the catalytic activity. Various works have established the dependency between the transition temperature of alumina and the surface area retention with the ionic size of the rare earth dopant [1-2, 4]. Kumar *et al* [4] demonstrated that alumina containing predominantly Ce³⁺ (ionic radius 1.034 Å) exhibits a higher surface area and transformation temperature compared to Ce⁴⁺ (ionic radius 0.92 Å). The differential scanning calorimetry (DSC) transformation temperature corresponding to the transition to α -Al₂O₃ increased by 100 °C in the case of Ce³⁺ doped γ -Al₂O₃. Hence, it should be expected that Ce³⁺-doped γ -Al₂O₃ nanowires can be utilised as a stable catalyst support for high temperature catalytic reactions.

Finally, the application of post-treatments on nanowires can lead to a number of metal and precious metal supported catalysts via impregnation methods (e.g Rh, Pt, Fe supported on Ce-doped γ -Al₂O₃ nanowires). Ce-doped alumina nanowires (support) can be decorated with a suitable active metal phase which can enhance industrially important reactions. An example of such a family of reactions is the steam reforming of aliphatic and aromatic molecules, used in the purification of gas streams and hydrogen production. It has been shown that these reactions can be facilitated by Ce-doped alumina (in the form of powder) supported-Fe catalysts [39].

4. Conclusions

(a) A novel sol-gel/hydrothermal pore sealing method has been employed to synthesise Ce-doped γ -Al₂O₃ nanowires. The nanowires have been synthesised in an AAO template via a method involving a 0.01M cerium nitrate:urea solution at a molar ratio of 1:40 followed by calcination at 500 °C for 5 hours. The nanowires were up to tens of microns in length, with diameters of 50 - 70 nm and exhibited a γ -Al₂O₃ grain size of 2-3 nm. Ce was incorporated within the nanowire in a 3+ oxidation state and was present at a concentration of < 1 at.%.

(b) The chemical processes leading to the formation of Ce-doped γ -Al₂O₃ nanowires have been fully described. Hydrothermal pore sealing of the cerium nitrate sol solution leads to the formation of Ce-doped AlOOH, which, upon calcination, is transformed into Ce-doped γ -Al₂O₃. Etching in 1M NaOH preferentially dissolves the amorphous anodic alumina template leaving free-standing Ce-doped γ -Al₂O₃ nanowires.

(c) A nanocrystalline CeO₂ thin film was also deposited on top of the AAO template. This layer had a cubic fluorite structure and average grain size 6-7 nm.

(d) With γ -Al₂O₃ being one of the most important alumina phases for catalytic applications, the synthesised Ce-doped nanowires are expected to have improved novel properties and potential applications in catalysis.

Acknowledgments

The authors would like to sincerely thank the Cyprus Research Promotion Foundation for funding this research under Cyprus-France Bilateral Project, No. Cy-Fr0907/2007 (Acronym: *NanoSens*) and the European Commission FP6 Marie Curie Actions, Project EXT-0023899 (Acronym: *NanoHeaters*).

References

- [1] Ozawa M, Kimura M and Isogai A 1990 Thermal stability and characterisation of γ -Al₂O₃ modified with rare earths *J. Less-Common Met.* **162** p 297
- [2] Kumar K N P, Tranto J, Kumar J and Engell J E 1996 Pore-structure stability and phase transformation in pure and M-doped (M=La, Ce, Nd, Gd, Cu, Fe) alumina membranes and catalyst supports *Mater. Sci. Lett.* **15** p 266
- [3] Wei Q, Chen Z-X, Wang Z-H, Hao Y-L, Zou J-X and Nie Z-R 2005 Effect of La, Ce, Y and B addition on thermal stability of unsupported alumina membranes *J. Alloys Compd.* **387** p 292
- [4] Kumar K-N P, Tranto J, Nair B N, Kumar J, Høj J W and Engell J E 1994 Effect of sintering atmosphere on the pore-structure stability of cerium doped nanostructured alumina *Mater. Res. Bull.* **29** p 551
- [5] Polychronopoulou K, Fierro J L G and Efstathiou A M 2004 The phenol steam reforming reaction over MgO-based supported Rh catalysts *J. Catal.* **28** p 417
- [6] Polychronopoulou K, Costa C N and Efstathiou A M 2004 The steam reforming of phenol reaction over supported-Rh catalysts *Appl Catal A* **272** p 37
- [7] Steele B C H 1999 Fuel-cell technology - Running on natural gas *Nature* **400** p 619
- [8] Corma A, Atienzar P, García H and Chane-Ching J-Y 2004 Hierarchically mesostructured doped CeO₂ with potential for solar-cell use *Nat. Mater.* **3** p 394
- [9] Masui T, Yamamoto M, Sakata T, Mori H and Adachi G 2000 **Synthesis of BN-coated CeO₂ fine powder as a new UV blocking material** *J. Mat. Chem.* **10** p 353
- [10] Jasinski P, Suzuki T and Anderson H U 2003 Nanocrystalline undoped ceria oxygen sensor *Sens. Actuators B* **95** p 73
- [11] Schem M, Schmidt T, Gerwann J, Wittmar M, Veith M, Thompson G E, Molchan I S, Hashimoto T, Skeldon P, Phani A R, Santucci S and Zheludkevich M L 2009 CeO₂ - filled sol-gel coatings for corrosion protection of AA2024-T3 aluminium alloy *Corros. Sci.* **51** p 2304
- [12] Hutleen J C and Martin C R 1997 A general template-based method for the preparation of nanomaterials *J. Mater. Chem.* **7** p 1075
- [13] Kuang D, Fang Y, Liu H, Frommen C and Fenske D 2003 Fabrication of boehmite AlOOH and γ -Al₂O₃ nanotubes via a soft solution route *J. Mater. Chem.* **13** p 660
- [14] Hou H, Xie Y, Yang Q, Guo Q and Tan C 2005 Preparation and characterization of γ -AlOOH nanotubes and nanorods *Nanotechnology* **16** p 741

- [15] Zhang J, Liu S, Lin J, Song H, Luo J, Elssfah E M, Ammar E, Huang Y, Ding X, Gao J, Qi S and Tang C 2006 Self-assembly of flower-like AlOOH (boehmite) 3-D nanostructures *J. Phys. Chem.* **110** p 14249
- [16] Lu C L, Lv J G, Xu L, Guo X F, Hou W F, Hu Y and Huang H 2009 Crystalline nanotubes of γ -AlOOH and γ -Al₂O₃: hydrothermal synthesis, formation mechanism and catalytic performance *Nanotechnology* **20** 215604
- [17] Xiao Z L, Han C Y, Welp U, Wang H H, Kwok W K, Willing G A, Hiller J M, Cook R E, Miller D J and Crabtree G W 2002 Fabrication of alumina nanotubes and nanowires by etching porous alumina membranes *Nano Lett.* **2** p 1293
- [18] Tian Y T, Meng G W, Gao T, Sun S H, Xie T, Peng X S, Ye C H and Zhang L D 2004 Alumina nanowire arrays standing on a porous anodic alumina membrane *Nanotechnology* **15** p 189
- [19] Sun X X, Liang J, Zhao J F, Ma Q and Xu B S 2010 Preparation of alumina nanowires, nanorods and nanowalls by chemical etching *Appl. Phys. A* **98** p 263
- [20] Jha H, Kikuchi T, Sakairi M and Takahashi H 2008 Synthesis of aluminium oxy-hydroxide nanofibers from porous anodic alumina *Nanotechnology* **19** 395603
- [21] Patermarakis G, Kerassovitou P (1992) Study on the mechanism of oxide hydration and oxide pore closure during hydrothermal treatment of porous of porous anodic Al₂O₃ films *Electrochim. Acta* **37** p 125
- [22] Patermarakis G, Moussoutzanis K and Chandrinos J 1999 Preparation of ultra-active alumina of designed porous structure by successive hydrothermal and thermal treatments of porous anodic Al₂O₃ *Appl. Catal. A* **180** p 354
- [23] Keijser Th H de, Mittemeijer E J and Rozendaal H C F 1983 The determination of crystallite-size and lattice-strain parameters in conjunction with the profile-refinement method for the determination of crystal structures *J. Appl. Crystallogr.* **16** p 309
- [24] Czerwinski F, and Szpunar J A 1997 The Nanocrystalline Ceria Sol-Gel Coatings for High Temperature Applications *J. Sol-Gel Sci. Technol.* **9** p 103
- [25] Ardelean H, Frateur I and Marcus P 2008 Corrosion protection of magnesium alloys by cerium, zirconium and niobium-based conversion coatings *Corros Sci.* **50** p 1907
- [26] Rao M V R and Shripathi T 1997 Photoelectron spectroscopic study of X-ray induced reduction of CeO₂ *J. Electron. Spectrosc. Relat. Phenom.* **87** p 121
- [27] Yan L, Xing X, Yu R, Deng J, Chen J and Liu G 2007 Facile alcohothermal synthesis of large scale ceria nanowires with organic surfactant assistance *Physica B* **390** p 59
- [28] Garvie L A J and Buseck P R 1999 Determination of Ce⁴⁺/Ce³⁺ in electron-beam-damaged CeO₂ by electron energy-loss spectroscopy *J. Phys. Chem. Solids* **60** p 1943
- [29] Garvie L A G, Xub H, Wang Y and Putnamd R L 2005 Synthesis of (Ca, Ce³⁺, Ce⁴⁺)₂Ti₂O₇: a pyrochlore with mixed-valence cerium *J. Phys. Chem. Solids* **66** p 902

- [30] Xu H and Wang Y 1999 Electron energy-loss spectroscopy (EELS) study of oxidation states of Ce and U in pyrochlore and uraninite $\pm$ natural analogues for Pu- and U-bearing waste forms *J. Nucl. Mater.* **265** p 117
- [31] H Mullejans and RH French, *J. Phys.D: Appl. Phys.* **29** (1996) 1751-1760
- [32] Wu G S, Xie T, Yuan X Y, Cheng B C and Zhang L D 2004 An improved sol-gel template synthetic route to large-scale CeO₂ nanowires *Mater. Res. Bull.* **39** 1023-1028
- [33] Thompson G E 1997 Porous anodic alumina: fabrication, characterization and applications *Thin Solid Films* **297** p 192
- [34] Yakovleva N M, Anicai L, Yakovlev A N, Dima L, Khanina E Ya, Buda M and Chupakhina E A 2002 Structural study of anodic films formed on aluminum in nitric acid electrolyte *Thin Solid Films* **416** p 16
- [35] Adachi-Pagano M, Forano C and Besse J-P 2003 Synthesis of Al-rich hydrotalcite-like compounds by using urea hydrolysis reaction-control of size and morphology *J. Mater. Chem.* **13** p 1988
- [36] Bokhimi X, Sánchez-Valente J and Pedraza F 2002 Crystallisation of sol-gel boehmite via hydrothermal annealing *J. Solid State Chem.* **166** p 182
- [37] Kaplyanski A A, Kulinkin A B, Kutsenko A B, Feofilov S P, Zakharchenya R I, and Vasilevskaya T N 1998 Optical spectra of triply-charged rare-earth ions in polycrystalline corundum *Phys. Solid State* **40** p 1310
- [38] Mardilovich P P, Govyadinoy A N, Mazurenko N I and Paterson R 1998 New and modified anodic alumina membranes part II - Comparison of solubility of amorphous (normal) and polycrystalline anodic alumina membranes *J. Membr. Sci.* **98** p 143
- [39] Polychronopoulou K, Bakandritsos A, Tzitzios V, Fierro J L G and Efstathiou A M 2006 Absorption-enhanced reforming of phenol by steam over supported Fe catalysts *J. Catal.* **241** p 132